

## DEUREX® TO 80 G

### TECHNICAL INFORMATION

<b>Chemical description:</b>	Oxidized Fischer-Tropsch-wax		
<b>Applications:</b>	<p><u>PVC and other plastics</u></p> <ul style="list-style-type: none"> <li>- Can be used in all U-PVC and P-PVC applications but also in C-PVC</li> </ul> <p>DEUREX® oxidized Hydrocarbon waxes are the best choice of lubricants especially in combination with calcium-zinc and tin stabilizers for rigid PVC products like window profiles, technical profiles, pipes and fittings.</p>		
<b>Properties:</b>	<p>Partially internal and external wax, highly effective wax</p> <ul style="list-style-type: none"> <li>- Accelerates fusion</li> <li>- Decreases torque and increases pressure</li> <li>- Synergistic effect in combination with non-polar PE waxes by reduction of melt viscosity</li> <li>- Useful in combination with tin stabilizers</li> <li>- Dust free</li> </ul>		
<b>Typical dosages:</b>	<p>Depending on the rheological requirements</p> <ul style="list-style-type: none"> <li>- up to 0.5 phr in combination with calcium-zinc</li> <li>- up to 1.0 phr in combination with tin stabilizers</li> </ul>		
<b>Technical data:</b>	Colour:	Off-white	
	Delivery form:	<b>DEUREX TO 80 G</b>	= Granules
		Minimum	Maximum
	Drop point*:	115 °C	120 °C
	Acid value*:	2 mgKOH/g	4 mgKOH/g
	Viscosity (140 °C):		20 mPas
	Penetration:		1.0 mm*10 <sup>-1</sup>
	Density (23 °C):	0.94 g/cm <sup>3</sup>	0.95 g/cm <sup>3</sup>
			Method
			LV 12 (DGF M-III 3)
			DIN EN ISO 2114
			LV 2 (DIN EN ISO3104)
			LV 4 (DIN 51579)
			LV 3 (DIN EN ISO 1183)
	* Part of certificate of analysis		
<b>Additional lubricants:</b>	<p><b>DEUREX® E 11 K</b> – Homopolymer PE-Wachs  <b>DEUREX® EO 40 K</b> – Oxidized LDPE wax  <b>DEUREX® EO 44 K</b> – Oxidized HDPE wax  <b>DEUREX® T 39 K</b> – Fischer Tropsch wax</p>		
<b>Alternative delivery form:</b>	<b>DEUREX® T 3901 W</b> – Fischer-Tropsch-wax emulsion		

## DEUREX<sup>®</sup> TO 80 G

DEUREX<sup>®</sup> TO 80 G was investigated in a calcium-zinc stabilized window profile formulation containing:

- 100 phr S-PVC (k=67)
- 15 phr coated calcium carbonate, window profile grade
- 4 phr titanium dioxide, rutile, window profile grade
- 6 phr acrylic impact modifier
- 4 phr calcium-zinc stabilizer

The dry blends were mixed up to 120°C in a high speed hot mixer and cooled down to 45°C. After a relaxation time of >12 hours the dry blend was extruded on a parallel twin screw extruder KMD 35-26.

The results are summarized in chart 1.

**Chart 1: Extrusion results** (rheological performance and basic data of the final profile)

		0.15 phr	0.15 phr			0.15 phr			0.15 phr	
	Blank	T49 prills	TO 80 prills	TO 81 prills	TO 82 prills	TO 83 prills	TO 84 prills	TP 406	PE E 18	ox PE EO 40
<b>Acid value of the wax (mg KOH/g)</b>		< 1	2 - 4	5 - 10	15 - 20	25 - 30	30 - 40	48 - 52	< 1	< 19
<b>Extrusion torque (%)</b>	54	48	48	50	51	56	61	63	51	59
<b>Pressures:</b>										
<b>M1 (bar)</b>	20	14	14	16	22	29	31	32	20	42
<b>M2 (bar)</b>	175	144	148	148	159	185	207	223	173	198
<b>M3 (bar)</b>	282	270	275	273	278	290	302	315	281	291
<b>M4 (bar)</b>	273	276	279	278	279	283	290	199	261	274
<b>Melt temperature (°C)</b>	198,1	196,4	196,4	196,7	197,1	198,3	199,1	199,2	196,3	200,3
<b>Output (kg/h)</b>	28,3	26,7	28,6	28,7	28,8	29,0	29,0	28,9	28,7	29,0
<b>DHC (min)</b>	41	42	42	42	42	42	41	41	41	40
<b>b*</b>	2,8	2,5	2,5	2,5	2,6	2,8	3,0	3,1	2,7	3,2
<b>Gloss (top)</b>	40,4	31,3	33,4	35,8	37,0	40,9	42,6	44,2	50,0	39,0
<b>Gloss (bottom)</b>	38,7	29,6	31,7	34,1	35,2	39,2	40,9	42,5	41,5	25,0

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

© - registered trademark by DEUREX

**Conclusions regarding oxidized FT waxes**

- **low oxidized Fischer-Tropsch-waxes** can be considered mainly as external waxes
  - they are close to standard FT waxes regarding their rheological behavior
  - due to their external behavior, low oxidized FT waxes help to delay fusion -  
this can be mainly seen by considering the pressure built up of the sensors M1 to M3 compared to the blank
  - low oxidized FT waxes are lowering the extrusion torque compared to the blank
  - there might be a slight increase of output in comparison to the standard FT wax
  - low oxidized FT waxes are also lowering the melt temperature compared to the blank
  - therefore the  $b^*$  value of the final profile is lowered in comparison to the blank
  - compared to standard FT waxes low oxidized FT waxes might slightly improve the gloss  
(the gloss of the specimen of the blank is higher due to the earlier gelation and the higher melt temperature)
  
  - **higher oxidized Fischer-Tropsch-waxes** are offering mostly the properties of internal waxes
  - they are close to oxidized LDPE waxes
  - regarding their rheological behavior higher oxidized FT waxes are closer to oxidized PE waxes than to standard FT waxes
  - higher oxidized FT waxes accelerate the fusion due to their behavior similar to oxidized PE waxes -  
this can be mainly seen by considering the pressure built up of the sensors M1 to M3 compared to the blank
  - higher oxidized FT waxes are increasing the extrusion torque compared to the standard FT wax
  - there might be a slight increase of output in comparison to the standard FT wax
  - higher oxidized FT waxes are increasing the melt temperature compared to the standard FT waxes
  - therefore the  $b^*$  value of the final profile is increased in comparison to the standard FT waxes
  - in comparison to standard FT waxes and to the blank higher oxidized FT waxes might slightly improve the gloss (this is mainly related to the earlier gelation and the higher melt temperature)
  
  - **oxidized Fischer-Tropsch-waxes at a lower oxidation degree** are a good alternative to PE waxes
  - they are keeping the stronger influence on torque at a lower dosage
  - PE waxes are mainly superior regarding their influence on gloss and lower melt viscosity, though higher loads of PE wax might be necessary to adjust the same extrusion torque
  
  - **oxidized Fischer-Tropsch-waxes at a higher oxidation degree** are a good alternative to oxidized LDPE waxes
- There might be a synergism in the combination of oxidized FT waxes and PE waxes.